



TECHNICAL DATA

ITEM: 704	
POLYESTER FILM GLASS YARN	
COLOR: Clear	
Adhesive: Pressure sensitive modified synthetic rubber resin.	
Adhesion to steel:	75 oz./in. width (82 N/100 mm width)
Tensile strength:	580 lbs./in.width (10,000 N/100 mm width)
Elongation to break:	4%
Total thickness:	6.0 mil (0.160 mm)
Standard widths:	1.9 in.(48 mm)
Storage conditions:	20-21 °C
Shelf life:	24 month

APPLICATION TECHNIQUES:

An extensive line of application equipment including hand-held dispensers and an automatic applicator is available. Application is most easily accomplished at room temperature. At lower temperatures, approaching 32°F (0°C), the adhesive becomes firm.

TECHNICAL INFORMATION:

The technical information recommendations and other statements contained in this document are based upon tests experience that believes are reliable, but the accuracy or completeness of such information is not guaranteed.

REMARKS:

The technical data is based on the reliable experiment carried by the company. Which however does not guarantee those properties and characteristics that are specified completely therein your purpose and condition to use this product upon your own responsibility.

www.magnifi-cent.com

**1010 Miramar Tower
132 Nathan rd.
Kowloon Hong Kong**

**Grand pitterson 132
high way
New Jersey USA**